

# Product Data Sheet

## AkzoNobel Powder Coatings Interpon D2525 Matt (25)

### Product Description

**Interpon D2525 Matt** is a series of ultra-durable powder coatings specifically formulated without TGIC, intended for use on architectural aluminium and galvanized steel. Providing new levels of weathering resistance **Interpon D2525 Matt** surpasses the performance of leading architectural powders. It offers significantly higher gloss retention and resistance to colour change combined with maximum film integrity to ensure long term cosmetic and functional protection.

These powder coatings are classified in Family I – class 6c under standard NFT 36-005.

**Interpon D2525 Matt** meets the requirements of GSB Master, Qualicoat Class 2, EN 12206 (formerly BS6496), EN13438 (formerly BS6497:1984) as well as AAMA 2604-13.

Some colours may not be available in Interpon D2525 Matt

Following Ral shades are excluded from the Ral families for Qualicoat class 2: Ral 1003, 1012, 1018, 1028, 1033, 2004, 2011, 3015, 3017, 3018, 3020, 4001

**Qualicoat License Number:** P-1210 (France), P-1212 (Italy), P-1201 (UK), P-1126 (Turkey)

**GSB License Number:** 183b (gloss 25)

### Powder Properties

|  |   |
|--|---|
| <b>Chemical type</b>                         | Polyester   |
| <b>Gloss (EN ISO 2813 (60°))</b>             | 20-30 gloss units   |
| <b>Particle Size</b>                         | Suitable for electrostatic spray  |
| <b>Specific gravity</b>                      | 1.2 – 1.9 g/cm <sup>3</sup> depending on colour                           |
| <b>Storage</b>                               | Dry cool conditions below 30°C ( <i>open boxes must be resealed</i> )     |
| <b>Shelf life</b>                            | 24 months below 30°C<br>12 months below 35°C                              |
| <b>Stoving schedule (Object Temperature)</b> | 15-30 minutes at 190°C<br>10-20 minutes at 200°C<br>8-16 minutes at 210°C |

### Test Conditions

The results shown below are based on mechanical and chemical tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for guidance only. Actual product performance will depend upon the circumstances under which the product is used.

|                           |  |
|---------------------------|--|
| <b>Substrate</b>          | Aluminium (0.5-0.8 mm Al Mg1)            |
| <b>Pretreatment</b>       | Chromate (DIN 50539)                     |
| <b>Dry Film Thickness</b> | 60 – 80 microns                          |
| <b>Stoving Schedule</b>   | 15 minutes at 200°C (object temperature) |

### Mechanical Tests

|                          |                               |                                     |
|--------------------------|-------------------------------|-------------------------------------|
| <b>Flexibility</b>       | ISO1519 (cylindrical Mandrel) | Pass Qualicoat class 2 requirements |
| <b>Adhesion</b>          | ISO2409 (2mm crosshatch)      | Gt0                                 |
| <b>Erichsen Cupping</b>  | ISO1520                       | Pass Qualicoat class 2 requirements |
| <b>Impact</b>            | ASTM D2794                    | Pass Qualicoat class 2 requirements |
| <b>Buchholz hardness</b> | ISO2815                       | >80                                 |

### Chemical Tests

|                               |              |   |
|-------------------------------|--------------|---|
| <b>Acetic acid salt spray</b> | ISO9227      | <16 mm <sup>2</sup> corrosion/10cm, 1000 hours              |
| <b>Constant humidity</b>      | ISO6270      | No blistering, creep <1mm (1000 hours)                      |
| <b>Sulphur Dioxide</b>        | ISO3231      | Pass 30 cycles – no blistering, gloss loss or discoloration |
| <b>Permeability</b>           | EN12206:2004 | Pressure Cooker – pass 1 hour - no defects                  |

## Interpon D2525 (Matt)

|                               |   |   |
|-------------------------------|---|---|
| <b>Chemical Resistance</b>    | Generally good resistance to acid, alkalis and oil at normal temperatures |   |
| <b>Mortar Resistance</b>      | EN12206-1   | No effect after 24 hours  |
| <b>Exterior durability</b>    | ISO2810   | Meets Qualicoat class 2 requirements after 3 years Florida<br>Meets AAMA 2604-13 requirements after 5 years Florida |
| <b>Accelerated Weathering</b> | ISO 11341 (1000 hrs)<br>QUV B 313 (600 hrs)                               | Gloss retention $\geq$ 90%<br>Gloss retention $\geq$ 50%  |

### Pretreatment

For maximum protection it is essential to pretreat components prior to the application of **Interpon D2525 Matt**.

Aluminium components should receive a full multi-stage chromate conversion coating or suitable chrome-free pre-treatment or suitable pre-anodising to clean and condition the substrate. Detailed advice should be sought from the pre-treatment supplier.

Galvanised steel requires surface preparation by either multi-stage pretreatment using either zinc phosphate or chromate conversion or controlled sweep blasting. Depending on the type of galvanizing, degassing or use of anti-bubbling additives may be required – follow the procedural advice of the pretreatment supplier.

**Interpon D2525 Matt** products may also be used on cast or mild steel. For outdoor use, **Interpon PZ** anti-corrosive primer over a correctly prepared substrate is recommended.

### Application

**Interpon D2525 Matt** powders can be applied by manual or automatic electrostatic spray or tribo-charging equipment. For solid shades, unused powder can be reclaimed up to a maximum of 30% using suitable equipment and recycled through the system. Please consult AkzoNobel for further details as to the correct mixing ratio for virgin/reclaim powder.

All powders can show small colour differences from batch to batch, this is normal and unavoidable. While AkzoNobel take every precaution to minimize visible differences, this cannot be guaranteed. Applicators and fabricators are advised to use a single batch for parts that will be assembled together. Differences are more likely with special effect powders.

Bonded products have better application properties than blended products (more stable) but attention should still be paid to line settings in order to avoid “marble effect” and changes in aspect after recycling. For more details it is suggested to read the ***Metallic Application Guideline***.

Different substrates (aluminium, steel, galvanized steel...), use of primer, and big changes in film thickness may give a different aspect.

Products with different codes should not be mixed even if same colour and gloss.

### Post Application

For specific advice on the suitability of post coating processes such as bending or the use of sealants, adhesives, thermal break, cleaning etc, please consult AkzoNobel.

### Maintenance

For specific advice on Cleaning and Maintenance, please consult the Interpon D series *Cleaning and Maintenance Guidelines* available from AkzoNobel.

### Safety Precautions

Please consult the Material Safety Datasheet (MSDS)

## Interpon D2525 (Matt)

---

### Disclaimer

### FOR PROFESSIONAL USE ONLY

**IMPORTANT NOTE:** The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel.

---

Akzo Nobel Powder Coatings Ltd. T +44 (0) 191 469 6111 For more information, contact your  
Worldwide Powder Group F +44 (0) 191 438 5431 local AkzoNobel representative  
Stoneygate Lane, Felling [www.interpon.com/contact-us](http://www.interpon.com/contact-us)  
Tyne & Wear  
NE10 0JY

Copyright © 2015 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel  
Interpon D2525 Matt - Issue 11  
Issued: 19/03/2015

**Interpon**®